PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6: C08L 7/02, C08J 5/18, C05F 17/02

(11) International Publication Number: **A1**

WO 99/48969

30 September 1999 (30.09.99) (43) International Publication Date:

(21) International Application Number:

PCT/EP99/02053

(22) International Filing Date:

18 March 1999 (18.03.99)

(30) Priority Data:

10-078743

Л 26 March 1998 (26.03.98)

(71) Applicant (for all designated States except US): ATOCHEM S.A. [FR/FR]; 4/8, cours Michelet, F-92080 Puteaux (FR).

(72) Inventors; and

(75) Inventors/Applicants (for US only): ISHINO, Kiyotaka [JP/JP]; Elf Atochem Japan Kyoto Technical Center, Science Center Building 3, Kyoto Research Park, 1 Chudoji Awato-cho, Shimogyo-ku, Kyoto-shi, Kyoto-fu, Kyoto 600 (JP). KURATSUJI, Takatoshi [JP/JP]; Elf Atochem Japan Kyoto Technical Center, Science Center Building 3, Kyoto Research Park, 1 Chudoji Awato-cho, Shimogyo-ku, Kyoto-shi, Kyoto-fu, Kyoto 600 (JP). YAMAMOTO, Jun [JP/JP]; Elf Atochem Japan Kyoto Technical Center, Science Center Building 3, Kyoto Research Park, 1 Chudoji Awato-cho, Shimogyo-ku, Kyoto-shi, Kyoto-fu, Kyoto 600 (JP). IKETAKI, Takashi [JP/JP]; Nishi 2-7, Inada-cho, Obihiro-shi, Hokkaido (JP).

(74) Agent: NEEL, Henry; ELF Atochem S.A., Dept. Propriété Industrielle, Cours Michelet - La Défense 10, F-92091 Paris La Défense Cedex (FR).

(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published

With international search report.

Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.

(54) Title: FILM FOR ACCELERATED COMPOST FERMENTATION

(57) Abstract

Objective: the objective of the present invention lies in shortening the compost preparation period by a simple method and preventing contamination of underground water. Constitution: film for accelerated compost fermentation which is characterized in that it comprises a composition in which the chief component is polymer containing polyether chains as structural units, and where the water vapour permeability thereof is at least 300 g/m2.24h, the oxygen permeability is at least 1,000 cm3/m2.24h.atm and the carbon dioxide permeability is at least 10,000 cm3/m2.24h.atm; together with film for accelerated compost fermentation which is characterized in that the aforesaid film is reinforced by means of a nonwoven material or net.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

						CT	Slovenia
AL	Albania	ES	Spain	LS	Lesotho	SI	
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MĐ	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	ľТ	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	zw	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zcaland		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
cz	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		
2525	Latonia						

WO 99/48969 PCT/EP99/02053

[Title of the Invention]

FILM FOR ACCELERATED COMPOST FERMENTATION

[Detailed Description of the Invention]

[0001] [Industrial Field of Application]

The present invention relates to film for accelerated compost fermentation. The objective thereof lies in shortening the fermentation period and preventing underground water pollution.

[0002] [Prior-Art]

Compost is obtained by aerobic microbial fermentation after mixing straw, rice chaff, weeds or the like with the excreta of domestic animals. Consequently, for obtaining a good quality compost it is necessary to have sufficient oxygen and a suitable level of temperature and moisture and, hitherto, the following methods have been adopted primarily.

First of all, in regard to the traditional method based on forming a heap, there has been the problem that, when the weather is fine, the surface dries out and hardens, so that air (oxygen) cannot readily pass into the interior and the fermentation is slowed, while, when it is raining, the moisture soaks into the interior, so that the composting materials are cooled and the fermentation is incomplete. Moreover, contaminated water soaks underground, which brings about the problem of under-ground water pollution.

[0003]

To overcome such difficulties, covering with polyvinyl chloride or polyethylene sheet has been tried to some extent but, with such sheet, not only is there a build-up of water vapour and carbon dioxide in the interior when the weather is fine but also the supply of oxygen is inadequate, so that aerobic fermentation by the micro-organisms is impeded and therefore the sheet has to be removed. However, at night, to cope with when it rains, it is necessary to cover over with the sheet again, so there is the problem of the nuisance of having to place and then remove the sheet.

[0004]

On the other hand, methods have been proposed using special apparatus and equipment, so that air is circulated and the temperature controlled, and these methods are to some extent being employed in practice (see, for example, Japanese Unexamined Patent Publication Nos 55-51788, 57-123883,

WO 99/48969 2 PCT/EP99/02053

60-260490, 3-237081, 3-261690, 4-59685, 5-170585, 7-277866, 7-98711 and 2524040).

At the same time, methods for accelerating fermentation using microbial decomposition accelerators have also been tried, as described in Japanese Unexamined Patent Publication No. 9-110571.

However, not only do these methods generally require equipment investment by the farmer, but also the procedure is complex and the equipment maintenance requires time, so a more simple, improved, method has been demanded.

[0005]

[Problem to be Resolved by the Invention]

The present inventors have carried out a painstaking investigation aimed at providing protection from rain-water by a simple method and shortening the fermentation time, as a result of which they have discovered that by using a film which is water impermeable but through which water vapour and gases can pass, this objective is realised. The present invention is based on this discovery.

[0006]

[Means for Resolving the Problem]

The present invention is a film for accelerated compost fermentation which is characterized in that it comprises a composition in which the chief component is polymer containing polyether chains as structural units, and the water vapour permeability thereof is at least 300 g/m2.24h, the oxygen permeability is at least 1,000 cm3/m2.24h.atm and the carbon dioxide permeability is at least 10,000 cm3/m2.24h.atm; together with film for accelerated compost fermentation which is characterized in that the aforesaid film is reinforced by means of a nonwoven material or net.

[0007]

In the present invention, "polymer containing polyether chains as structural units" refers to a block copolymer in which polyoxyalkylene chains and other polymer chains are linked together, or polymer in which polyoxyalkylene chains are linked together via connecting regions. As examples of the polyoxyalkylene here, there are poly-oxyethylene, poly(1,2- and 1,3-oxypropylene), polyoxytetramethylene, polyoxyhexamethylene, block or random copolymers of ethylene oxide and propylene oxide, and block or random copolymers of ethylene oxide and tetra-hydrofuran. In particular, it is preferred that the number of carbons in the alkylene moiety be from 2 to 4, with polyoxyethylene being most preferred. The number average molecular weight of the polyoxyalkylene is from 200 to 6000, and preferably from 300 to 4000.

WO 99/48969 PCT/EP99/02053

180001

In the present invention, as examples of desirably used "polymer containing polyether chains as structural units" there are polyetherpolyamide block copolymers, polyether-polyester block copolymers and polyetherurethanes. Of these, the polyetherpolyamide block copolymers are particularly preferred.

[0009]

The "polyetherpolyamide block copolymers" used in the present invention are polymers in which there are linked together polyoxyalkylene chains (a) and polyamide chains (b) which are the polymers of aminocarboxylic acids or lactams with 6 or more carbon atoms, or of the salts of dicarboxylic acids and diamines with 6 or more carbon atoms. Where (a) and (b) are mutually connected via a dicarboxylic acid (c) having from 4 to 20 carbons, the polymer is generally referred to as a polyetherester-amide, and such polymer is also included. Here, as the "aminocarboxylic acids or lactams with 6 or more carbon atoms, or salts of dicarboxylic acids and diamines with 6 or more carbon atoms", 11aminoundecanoic acid, 12-aminododecanoic acid, caprolactam, laurolactam, the adipic acid and hexamethylenediamine + hexamethylenediamine + sebacic acid are preferably used. Again, there may be jointly used two or more types of aforesaid components (a) and (b).

[0010]

Such polymer may be produced, for example, by the method described in Japanese Examined Patent Publication No. 56-45419. The type and weight ratio of the polyether component and the polyamide component in the block copolymer used in the present invention are selected according to the objectives and the application. From the point of view of water vapour permeability, gas permeability, water resistance and handling properties, etc, the ratio of the polyether/polyamide is preferably from 4/1 to 1/4.

[0011]

The "polyetherpolyester block copolymer" used in the present invention is one in which there are linked together polyoxyalkylene chains (a) and polyester chains (d) comprising polymer of a hydroxycarboxylic acid with at least six carbons or of a dihydroxy compound with at least two carbons and an aromatic dicarboxylic acid. Again, in regard to these (a) and (d) components, two or more types may be jointly employed. Such polymer is produced for example by the method described in US Patent 4,739,012. The weight ratio of the aforesaid (a) and (d) components in the block copolymer employed in the present invention is determined by the objectives and the application.

[0012]

The 'polyetherurethane' employed in the present invention is a thermoplastic polyurethane employing polyether as the soft segments, but there is little effect with a polyester type or caprolactone type even though they are also polyurethanes. Specifically, the polyurethanes are normally obtained by the reaction of an organic diisocyanate and a polyether of molecular weight from

WO 99/48969 4 PCT/EP99/02053

500 to 6000 with, in some cases, the chain extension being carried out in the presence of catalyst. As the isocyanate, there is preferably employed tolylene diisocyanate, diphenylmethane diisocyanate or the like, and as the polyether there is preferably used polytetramethylene glycol or polypropylene oxide, etc.

[0013]

In the present invention, "composition in which the chief component is polymer containing polyether chains as structural units" means a polyetherpolyamide block copolymer, polyetherpolyester block copolymer or polyetherurethane on its own, a mixture of these, or, in the case of the block copolymers, mixtures of two types of polymer in which the resin soft segment/hard segment type or content differs. It also includes blends with some other resin. As examples of the resins which can be blended to produce the composition, there are polyolefins such as polyethylene and the copolymers of polyethylene and acrylate. In the case where blending is carried out with another resin, there may also be incorporated a compatibilizing agent such as an ethylene copolymer or graft copolymer with unsaturated epoxy groups or acid anhydride groups, or an acrylate copolymer.

The type and ratio of the resin other than the polymer with polyether structural units will be selected such that the water vapour and gas permeabilities lie within the following ranges.

[0014]

The film of the present invention needs to have a water vapour permeability of at least 300 g/m2.24h, an oxygen permeability of at least 1,000 cm3/m2.24h.atm and a carbon dioxide permeability of at least 10,000 cm3/m2.24h.atm. Preferably, the water vapour permeability is at least 1000 g/m2.24h, the oxygen permeability is at least 3,000 cm3/m2.24h.atm and the carbon dioxide permeability is at least 30,000 cm3/m2.24h.atm, and more preferably the water vapour permeability is at least 2000 g/m2.24h, the oxygen permeability is at least 5,000 cm3/m2.24h.atm and the carbon dioxide permeability is at least 50,000 cm3/m2.24h.atm.

[0015]

If the water vapour permeability is less than 300 g/m2.24h, then the interior moisture will increase. If the carbon dioxide permeability is less than 10,000 cm3/m2.24h.atm, there is a build-up of carbon dioxide gas in the interior and if the oxygen permeability is less than 1,000 cm3/m2.24h.atm, then there is an insufficient supply of oxygen to the interior, so that anaerobic fermentation occurs and a good quality compost is not obtained.

[0016]

In the composition in which the chief component is polymer containing polyether chains as structural units, there may be freely included known antioxidants, thermal decomposition preventives, ultraviolet absorbers, hydrolysis resistance improvers, colouring agents (dyes and pigments), antistatic agents, electro-

WO 99/48969 5 PCT/EP99/02053

conductors, crystallization nucleating agents, crystallization promoters, plasticizers, ready slip agents, lubricating agents, release agents, flame retardants and flame retarding auxiliaries, within a range such that the characteristics of the present invention are not impaired. In regard to the method for producing film from this composition, there can be used the T-die extrusion method or the inflation method, with film formation being conducted by passage through a T-die or an inflation die, etc. The extrusion temperature will depend on the resin type and the blending ratio but, in general, it is from 120 to 250°C.

[0017]

The film of the present invention is mostly used outdoors, so in cases where strength is required it is still more effective to carry out reinforcement with a nonwoven material or net. As the nonwoven material, there can be used one which comprises polyamide or polyester fibre. A polyolefin net or the like can also be used.

In the case of a nonwoven material or net, a two layer structure (with the nonwoven material or net on the outside) or a three layer structure (with the film interposed between nonwoven material or net) may be used. However, it is necessary to select a material, form and thickness such that the water vapour and gas permeability are not impaired.

[0018] [Examples]

Below, the present invention is explained by means of examples but it goes without saying that the present invention is not to be restricted just to these. Now, in the examples, the various properties were measured by the following methods.

(1) Water vapour permeability (units: g/m2.24h)

The film was subjected to measurement under conditions B (40°C, 90% relative humidity) based on JIS Z0208.

(2) Gas permeability (units: cc/m2.24h.atm or %)

Measurement was carried out by the pressure difference method. The specific conditions were as follows.

Equipment: gas permeability measurement device model GTR-10XE produced by the Yanako Bunseki Kogyo (Co.).

Measurement area: 15.2 cm2 (44 mm diameter)

Detection method: calibration curve method based on a gas chromatograph fitted with a TCD

WO 99/48969 6 PCT/EP99/02053

Temperature, relative humidity: 25°C, 0% RH

Carrier gas: helium, 70 KPa

Diffusion gas: CO2/O2/N2/C2H4 (30.0/30.0/39.12/0.88 vol%)

[0019]

Further, the films employed in the present invention were as follows.

A-1: Film of thickness 25 microns comprising polyetherester-polyamide block copolymer consisting of polyoxyethylene chains and polyamide 12 chains (weight ratio 1/3)

The permeabilities of this film were as follows.

water vapour permeability: 5,100 g/m2.24h oxygen permeability: 3,700 cm3/m2.24h.atm

carbon dioxide permeability: 55,000 cm3/m2.24h.atm

A-2: Film of thickness 25 microns comprising a composition consisting of polyetherester-polyamide block copolymer composed of polyoxyethylene chains and polyamide 12 chains (weight ratio 1/1), and ethylene-butyl acrylate copolymer, (weight ratio of composition = 65/35)

The permeabilities of this film were as follows.

water vapour permeability: 4,000 g/m2.24h oxygen permeability: 109,000 cm3/m2.24h.atm carbon dioxide permeability: 27,000 cm3/m2.24h.atm

- A-2: Film A-2 laminated and reinforced with a polyamide 6 nonwoven
- B-2: Commercial plasticized vinyl chloride film for agriculture

water vapour permeability: 40 g/m2.24h oxygen permeability: 1,800 cm3/m2.24h.atm

carbon dioxide permeability: 12,000 cm3/m2.24h.atm

[0020]

[Example 1, Comparative Example 1]

Composts were prepared in five sections, in each of which had been compressed compost material comprising straw mixed with cow dung to a size of height about 2 m, width about 3 m and length about 20 m, and covered respectively with A-1, A-2, A-3, B-1 and B-0 [compost heap with no film]. Now, excepting that turning of the heap was carried out every month, they were left covered with the film. On each such occasion, the compost weight and the compost

WO 99/48969 7 PCT/EP99/02053

composition (moisture, organic material and chief inorganic materials content) were measured. Further, the temperature of the compost was monitored with a temperature sensor.

In the case of the A-1, A-2 and A-3 composts, at the time of the third monthly turning of the heap, the straw had decomposed for the most part and it was concluded that the fermentation had proceeded fully. Now, when exposed to a strong wind, A-2 was seen to have suffered some damage, but no damage was noted for A-3 which was reinforced with a nonwoven material.

Table 1 shows the change in compost weight, moisture content and temperature for A-1, B-0 and B-1.

[Table 1]

Change in Compost Weight, Moisture and Temperature

A-1	B-0	B-1
100	100	100
81	87	89
74	85	84
62	84	76
66	62	70
60	67	66
65	63	65
64	65	67
40-60	45-65	30-55
35-58	25-55	30-45
20-40	3-35	20-30
	100 81 74 62 66 60 65 64 40-60 35-58	100 100 81 87 74 85 62 84 66 62 60 67 65 63 64 65 40-60 45-65 35-58 25-55

¹⁾ The weight at 0 month being taken as 100%

From Table 1, the weight reduction was most rapid in section A-1 compared to the others. This was because the water vapour permeability was high but there was no penetration of rain water. Furthermore, the moisture content was largely kept constant at a suitable level, and the temperature too moved within a reasonable range of 40-60°. For these reasons, it is concluded that microbial fermentation occurred rapidly. Moreover, in terms of the weight reduction, since after 3 months this had already reached the same level as ordinary completely composted material, it was concluded that the fermentation was complete. On the other hand in the case of section B-1, since the moisture vapour permeability was low, moisture evaporation was suppressed and the reduction in weight was

slow. Moreover, since the temperature was low, it is thought that there was little heat evolution due to aerobic fermentation by the micro-organisms. Table 2 shows the compositions of the composts after 3 months for A-1, B-0 and B-1.

[Table 2] Compost Composition

	A-1	B-0	- B-1	Good Compost
total carbon (%)	24.5	23.3	26.5	30-40
total nitrogen (%)	2.2	1.8	1.9	≥2.2
CaO (%)	2.9	2.5	2.7	≥2.4
K ₂ O (%)	4.2	4.1	4.5	≥4.0
electrical conductivity ms/cm.s	8.2	6.7	7.1	≥7.8

From Table 2, it can be seen that although the total carbon in section A=1 was slightly low, the total nitrogen exceeded 2% and the CaO and K_2O were at least the specified values, while electrical conductivity which indicates activity was 8 ms/cm.s, and so a good compost was obtained. On the other hand, in the case of B-O and B-1, the total nitrogen and the electrical conductivity were low and a good compost was not obtained after 3 months.

[0021]
[Effects of the Invention]

As explained above, by employing film through which water does not pass but through which water vapour and gas can permeate, the present invention offers simple protection against rainwater and shortens the fermentation period.

WO 99/48969 9 PCT/EP99/02053

[Scope of Claims]

[Claim 1] Film for accelerated compost fermentation which is characterized in that it comprises a composition in which the chief component is polymer containing polyether chains as structural units, and the water vapour permeability thereof is at least 300 g/m2.24h, the oxygen permeability is at least 1,000 cm3/m2.24h.atm and the carbon dioxide permeability is at least 10,000 cm3/m2.24h.atm.

[Claim 2] Film according to Claim 1 which is characterized in that the polymer containing polyether chains as structural units is of at least one type selected from the group comprising polyetherpolyamide block copolymers, polyetherpolyester block copolymers and polyetherurethanes.

[Claim 3] Film according to Claim 1 where the film of Claim 1 is reinforced by means of a nonwoven material or net.




Inter onal Application No PCT/EP 99/02053

		1 , 0 , 7 2 .	33,02033
A CLASSI IPC 6	FICATION OF SUBJECT MATTER C08L71/02 C08J5/18 C05F17	7/02	
According to	o International Patent Classification (IPC) or to both national classi	fication and IPC	
	SEARCHED		
Minimum do IPC 6	commentation searched (classification system followed by classific COSL COSJ COSG COSF	ation symbols)	
Documenta	ion searched other than minimum documentation to the extent tha	t such documents are included in the fields	searched
	ata base consulted during the international search (name of data t	pase and, where practical, search terms use	rd)
	ENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the re	elevant passages	Relevant to claim No.
х	US 5 660 887 A (NUSSBAUMER WALTI 26 August 1997 (1997-08-26) claim 1 column 3, line 32	ER ET AL)	1-3
X	KAPLAN W A ET AL: "THE EFFECT OF STRUCTURE ON THE GAS PERMEABILITY POLYURETHANES" JOURNAL OF CELLULAR PLASTICS, vol. 30, no. 3, 1 May 1994 (1994) pages 242-272, XP000443643 ISSN: 0021-955X tables 2A,B	TY OF MODEL	1,2
X	EP 0 378 015 A (ATOCHEM ELF SA) 18 July 1990 (1990-07-18) claim 1	-/	1,2
X Furth	er documents are listed in the continuation of box C.	Patent family members are listed	in annex.
"A" document consider the consider of filing de "L" document which is citation of the rest of the constant	it which may throw doubts on priority claim(s) or s cited to establish the publication date of another or other special reason (as specified) int referring to an oral disclosure, use, exhibition or	To later document published after the integer or priority date and not in conflict with oited to understand the principle or the invention. "X" document of particular relevance; the coannot be considered novel or cannot involve an inventive step when the document of particular relevance; the coannot be considered to involve an involve an involve an involve an involve an involve and coument is combined with one or moments, such combined with one or moments, such combination being obvious in the art. "&" document member of the same patent to Date of mailing of the international sea.	the application but sarry underlying the statement invention be considered to current a taken alone laimed invention rentive step when the re-other such docurs to a person skilled family
22	? July 1999	1 2. 08. 1999	
Name and m	siling address of the ISA European Patent Office, P.B. 5818 Patentiaan 2 NL - 2280 HV Riperijk Tel. (+31-70) 340-240, Tx. 31 651 epo nl, Fax: (+31-70) 340-3416	Authorized officer 0'Sullivan, T	

2





		PC1/EP 99/02053			
	(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT				
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.			
(DE 44 40 837 A (BASF AG) 23 May 1996 (1996-05-23) claim 1 page 8, line 65 - line 66	1,2			
	US 3 895 916 A (ROSNER KURT) 22 July 1975 (1975-07-22) figures 1-4	1-3			
1					

2



Information on patent family members

Int ational Application No PCT/EP 99/02053

				- FCI/LI	99/02053
Patent document cited in search report		Publication date		Patent family member(s)	Publication date
US 5660887	A	26-08-1997	DE US AT CA DE DE EP JP MS US	4121716 A 5883217 A 179450 T 2072839 A 4143454 C 59209682 D 0522321 A 5209162 A 9203828 A 5869593 A 5851661 A 5508371 A	14-01-1993 16-03-1999 15-05-1999 02-01-1993 05-01-1995 02-06-1999 13-01-1993 20-08-1993 01-03-1993 09-02-1999 22-12-1998 16-04-1996
EP 0378015	A	18-07-1990	FR AU CA CN CDE DK ES FI GR HE JP KR NO PT US	2639644 A 117333 T 627523 B 4547889 A 2003489 A,C 1042926 A,B 1096308 A,B 68920724 D 68920724 T 591289 A 2066872 T 99130 B 3015515 T 177795 A 70669 B 92304 A 2199131 A 2572135 B 9311366 B 305321 B 92402 A,B 5506024 A	01-06-1990 15-02-1995 27-08-1992 31-05-1990 25-05-1990 13-06-1990 14-12-1994 02-03-1995 24-08-1995 26-05-1990 16-03-1995 30-06-1997 30-06-1995 01-12-1995 11-12-1996 25-01-1994 07-08-1990 16-01-1997 04-12-1993 10-05-1999 31-05-1990 09-04-1996
DE 4440837	A	23-05-1996	AU AU CA CN CZ WO EP FI HU JP NO NZ PL	691317 B 2978195 A 2205072 A 1170419 A 9701465 A 9615174 A 0792310 A 972060 A 77057 A 11500468 T 972227 A 289823 A 320223 A	14-05-1998 06-06-1996 23-05-1996 14-01-1998 15-10-1997 23-05-1996 03-09-1997 14-05-1997 02-03-1998 12-01-1999 14-07-1997 26-06-1998 15-09-1997
US 3895916	A	22-07-1975	AT AU BE CA CH DE FR GB	319287 B 5599173 A 799009 A 976779 A 587202 A 2226729 A 2186405 A 1381848 A	10-12-1974 28-11-1974 31-08-1973 28-10-1975 29-04-1977 13-12-1973 11-01-1974 29-01-1975





Information on patent family members

int	tional	Application No
PCT	/EP	99/02053

Patent document aited in search report	Publication date	Patent family member(s)	Publication date
US 3895916 A		JP 1005335 C JP 49084857 A JP 54037230 B NL 7306629 A,C	24-07-1980 14-08-1974 14-11-1979 04-12-1973